

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-37. (canceled)

38. (Withdrawn) A method for the production of a powder comprising essentially spherical particles of an aromatic polyether ketone plastic, comprising: mixing a matrix micropowder into a liquid phase to form a suspension wherein the particle size of the matrix micropowder is less than the particle size of the powder; spraying the suspension through a nozzle to form droplets comprising the matrix micropowder; and vaporizing or evaporating a liquid component from the droplets to form the powder in the form of essentially spherical agglomerates.

39. (Withdrawn) The method according to claim 38, wherein the liquid phase is further mixed with at least one of a reinforcing fiber or a stiffening fiber having a length less than the particle size of the powder.

40. (Withdrawn) The method according to claim 38, wherein the matrix micropowder has an average grain size d_{50} between 3 and 10 μm .

41. (Withdrawn) The method according to claim 38, wherein the matrix micropowder has an average grain size d_{50} of 5 μm .

42. (Withdrawn) The method of claim 39, wherein the fibers have an average length L50 of 20 to 150 μm .

43. (Withdrawn) The method according to claim 39, wherein the fibers have an average length L50 of 40 to 70 μm .

44. (Withdrawn) The method according to claim 39, wherein the matrix micropowder has an average grain size d_{50} between 3 and 10 μm and the fibers have an average length L50 of 10 to 100 μm .

45. (Withdrawn) The method according to claim 39, wherein the matrix micropowder has an average grain size d_{50} of 5 μm and the fibers have an average length L50 of 10 to 80 μm .

46. (Withdrawn) The method according to claim 38, wherein the droplets have an average diameter d_{50} of 10 to 70 μm .

47. (Withdrawn) The method according to claim 38, wherein the vaporizing or evaporating is carried out with the droplets are moving through a heating segment.

48. (Withdrawn) A method for the production of a powder comprising a first component in the form of essentially spherical powder particle or least one of a stiffening fiber or a reinforcing fiber wherein the first component comprises a matrix material, and the fibers are powder particles, comprising mixing a matrix micropowder with a liquid phase to form a suspension wherein the particle size of the matrix micropowder is less than the particle size of the powder; spraying the suspension through a nozzle to form droplets comprising the matrix micropowder; and vaporizing or evaporating a liquid component from the droplets to form the powder in the form of essentially spherical agglomerates,

49. (Withdrawn) The method according to claim 48, wherein the liquid phase is further mixed with at least one of a reinforcing fiber or a stiffening fiber having a length less than the particle size of the powder.

50. (Withdrawn) The method according to claim 48, wherein the matrix micropowder has an average grain size d_{50} between 3 and 10 μm .

51. (Withdrawn) The method according to claim 48, wherein the matrix micropowder has an average grain size d_{50} of 5 μm .
52. (Withdrawn) The method of claim 48, wherein the fibers have an average length L50 of 20 to 150 μm .
53. (Withdrawn) The method according to claim 48, wherein the fibers have an average length L50 of 40 to 70 μm .
54. (Withdrawn) The method according to claim 49, wherein the matrix micropowder has an average grain size d_{50} between 3 and 10 μm and the fibers have an average length L50 of 10 to 100 μm .
55. (Withdrawn) The method according to claim 49, wherein the matrix micropowder has an average grain size d_{50} of 5 μm and the fibers have an average length L50 of 10 to 80 μm .
56. (Withdrawn) The method according to claim 48, wherein the droplets have an average diameter d_{50} of 10 to 70 μm .
57. (Withdrawn) The method according to claim 48 wherein the vaporizing or evaporating is carried out while the droplets are moving through a heating segment.
58. (Withdrawn) A method for the production of a powder comprising essentially spherical particles of an aromatic polyether ketone plastic, comprising: cooling a coarse granulate comprising a plastic matrix material to form brittle, coarse granulates; grinding the brittle, coarse granulates; and separating the ground granulate into a fraction spectrum.
59. (Withdrawn) The method according to claim 58, wherein the coarse granulate is a fiber-reinforced plastic matrix material.

60. (Withdrawn) The method according to claim 58, wherein the grinding is carried out with a pinned disk mill.
61. (Withdrawn) The method according to claim 58, wherein the grinding is carried out with cooling.
62. (Withdrawn) The method according to claim 58, wherein the separating is carried out with an air separator.
63. (Withdrawn) The method according to claim 58, further comprising: smoothing the ground granulate.
64. (Withdrawn) The method according to claim 63, wherein the smoothing is carried out by embedding or accumulating at least one of microparticles or nanoparticles.
65. (Withdrawn) A method for producing a powder comprising a first component in the form of essentially spherical powder particles and at least one of a stiffening fiber or a reinforcing fiber, wherein the first component comprises a matrix material, comprising: cooling a coarse granulate comprising a plastic matrix material to form brittle, coarse granulates; grinding the brittle, coarse granulates; and separating the ground granulate into a fraction spectrum.
66. (Withdrawn) The method according to claim 65, wherein the coarse granulate is a fiber-reinforced plastic matrix material.
67. (Withdrawn) The method according to claim 65 wherein the grinding is carried out with a pinned disk mill.
68. (Withdrawn) The method according to claim 65, wherein the grinding is carried out with cooling.

69. (Withdrawn) The method according to claim 65, wherein the separating is carried out with an air separator.
70. (Withdrawn) The method according to claim 65, further comprising smoothing the ground granulate.
71. (Withdrawn) The method according to claim 70, wherein the smoothing is carried out by embedding or accumulating at least one of microparticles or nanoparticles.
72. (Previously presented) A method for producing a powder comprising essentially spherical particles of an aromatic polyether ketone plastic, comprising:
 - melting a matrix material;
 - blowing the melted matrix material through a nozzle to form droplets; and
 - passing the droplets through a cooling segment.
73. (Previously presented) The method according to claim 72, further comprising:
 - stirring at least one of stiffening fibers or reinforcing fibers into the melted matrix material before blowing the melted matrix material.
74. (Previously presented) The method according to claim 72, wherein the droplets are formed in a hot gas jet.
75. (Previously presented) The method according to claim 72, further comprising:
 - separating the cooled droplets into a fraction spectrum.

76. (Previously presented) A method for producing a powder comprising a first component in the form of essentially spherical powder particles and at least one of a stiffening fiber or a reinforcing fiber, wherein the first connection comprises a matrix material, comprising:

- melting a matrix material;
- blowing the melted matrix material through a nozzle to form droplets; and
- passing the droplets through a cooling segment.

77. (Previously presented) The method according to claim 76, further comprising:
stirring at least of stiffening or reinforcing fibers into the melted matrix material before blowing the melted matrix material.

78. (Previously presented) The method according to claim 76, wherein the droplets are formed in a hot gas jet.

79. (Previously presented) The method according to claim 76, further comprising:
separating the cooled droplets into a fraction spectrum.

80. (Withdrawn) A method for producing a spatial structure, comprising: melting the powder according to claim 38.

81. (Withdrawn) The method according to claim 80, wherein melting includes powder-based generative rapid prototyping, selective laser sintering or laser melting.

82. (Withdrawn) A method for producing a spatial structure, comprising: melting the powder according to claim 48.

83. (Withdrawn) The method according to claim 82, wherein melting includes powder-based generative rapid promoting, selective laser sintering or laser melting.

84. (Withdrawn) A molded body obtained by powder-based generative rapid prototyping of the powder according to claim 38.

85. (Withdrawn) The molded body of claim 84, wherein the powder-based generative rapid prototyping is selective laser sintering or laser melting.

86. (Withdrawn) A molded body obtained by powder-based generative rapid prototyping of the powder according to claim 38.

87. (Withdrawn) The molded body of claim 86, wherein the powder-based generative rapid prototyping is selective laser sintering or laser melting.

88. (Withdrawn) The molded body according to claim 84, comprising one or more interior reinforcements.

89. (Withdrawn) The molded body according to claim 84, comprising a three-dimensional framework reinforcement.

90. (Withdrawn) The molded body according to claim 86, comprising one or more interior reinforcements.

91. (Withdrawn) The molded body according to claim 86, comprising a three-dimensional framework reinforcement.

92. (Withdrawn) A molded body obtained by powder-based generative rapid prototyping of the powder according to claim 38.

93. (Withdrawn) The molded body of claim 92, wherein the powder-based generative rapid prototyping is selective laser sintering or laser melting.

94. (Withdrawn) The molded body according to claim 93, comprising one or more interior reinforcements.